

Description

SUPAPATCH S is a high strength multi-purpose patching and repair mortar. Once applied the product is dark grey in colour

Principal uses

- Structural repairs to concrete
- Restoration of spalled and damaged concrete
- Repairs to honeycomb

Advantages

- Easy to mix, apply and finish
- Excellent adhesion
- Shrinkage compensated

Performance data

Property	Typical results		
Compressive strength	24 hours	14days	28days
Mixed to a 50mm slump	10Mpa	32Mpa	34Mpa

Early Height Change Positive
 Hardened height Change Positive
 Bond strength ASTM C-882 >12

Workability

Once mixed the product is smooth to allow for easy application

Surface preparation

Concrete substrate must be structurally sound. Remove all oil, grease, paint, corrosion, a dust and surface deposits. This can be done by wire brush or sand blasting. Ensure surface is wet or prime with Plaster Key to improve bond consistency required

Limitations

Do not use if temperatures are below 9°C. Avoid

excessive heat 35°C and higher, wet hessian may be used to reduce heat or use curing compounds to improve performance

Mixing instructions

Pre wet concrete mixer, add between 3L and 4.5L of water into the mixer, depending on the add the contents of the bag and mix until desired slump is achieved

Yield

Mixed with 4L of water will yield 12L

Set time

Water content	Initial set	Final set
4L per 25kg	2 hours	3 hours

Packaging

SUPAPATCH S is available in 25kg bags

Safety & handling

Wear dust masks when mixing. Use gloves, eye protection at all times. Should the product come into contact with eyes, wash immediately and seek medical advice

Shelf Life & Storage

12 months when stored in a cool dry place, failure to comply with these recommendations will result in a reduction in shelf life

Note

For increased adhesion capabilities prime the surface with a mixture of cement, river sand and Plaster key. For further instruction please consult your local representative for a method statement on the product

Note: The information and specifications provided is to the best of our knowledge. The technical data contained herein are true and accurate at the date of issue and are subject to change without prior notice. No guarantee of accuracy is given or implied. We guarantee our products to conform to ASHAK Construction Chemicals quality control. We cannot be held responsible or liable, directly or in directly for the use of our products, coverage, performance or injury resulting from use, as we have no control over the method of application used or site conditions. For further technical and method statements, contact our Technical representatives.